

**Listing of Claims:**

Claim 1 (previously presented): A cathode comprising:

a cathode mixture layer including a cathode active material and a binder, the binder including a styrene butadiene latex adhesive and a thickener wherein the content of the styrene butadiene latex adhesive in the cathode mixture layer ranges from about 2 wt% to about 4 wt%, the content of the thickener in the cathode mixture layer ranges from about 0.5 wt% to about 2.5 wt%, and the thickener is polyacrylic acid, wherein the cathode active material includes a lithium iron phosphorous oxide that has an olivine structure.

Claim 2 (canceled)

Claim 3 (previously presented): The cathode according to claim 1, wherein the cathode mixture layer includes a carbon material as a conductive agent and wherein the content of the carbon material ranges from about 5 wt% to about 12 wt% with respect to the total amount of the cathode active material and the carbon material.

Claim 4 (withdrawn): A cathode comprising:

a cathode mixture layer including a cathode active material and a binder, the binder including maleic acid-denaturalized polyvinylidene fluoride wherein the content of the maleic acid-denaturalized polyvinylidene fluoride in the cathode mixture layer ranges from about 0.5 wt% to about 4 wt%.

Claim 5 (withdrawn): The cathode according to claim 4, wherein the amount of the maleic acid-denaturalized polyvinylidene fluoride ranges from about 0.1 wt% to about 0.4 wt%.

Claim 6 (withdrawn): The cathode according to claim 4, wherein a part of the maleic acid-denaturalized polyvinylidene fluoride is substituted with hexafluoro propylene having a substitution ratio that is about 5 wt% or less.

Claim 7 (withdrawn): The cathode according to claim 4, wherein the cathode active material includes a lithium phosphorous oxide that has an olivine structure.

Claim 8 (withdrawn): The cathode according to claim 4, wherein the cathode mixture layer contains a conductive agent, and wherein the content of the carbon material ranges from about 5 wt% to about 12 wt% with respect to the total amount of the cathode active material and the carbon material.

Claim 9 (previously presented): A battery comprising:  
a cathode, the cathode including a cathode mixture layer containing a cathode active material, and a binder including a styrene butadiene latex adhesive and a thickener;  
an anode; and  
an electrolyte,

wherein the content of the styrene butadiene latex adhesive in the cathode mixture layer ranges from about 2 wt% to about 4 wt%, wherein the content of the thickener in the cathode mixture layer ranges from about 0.5 wt% to about 2.5 wt% and the thickener is polyacrylic acid, and wherein the battery has a charge final voltage of about 4.0 V or less, wherein the cathode active material includes a lithium iron phosphorous oxide that has an olivine structure.

Claim 10 (canceled)

Claim 11 (previously presented): The battery according to claim 9, wherein the cathode mixture layer contains a conductive agent including a carbon material, and wherein the content of the carbon material ranges from about 5 wt% to about 12 wt% with respect to the total amount of the cathode active material and the carbon material.

Claim 12 (withdrawn): A battery comprising:  
a cathode, the cathode including a cathode active material and a binder including a maleic acid-denaturalized polyvinylidene fluoride;  
an anode; and  
an electrolyte,

wherein the content of the maleic acid-denaturalized polyvinylidene fluoride in the cathode mixture layer ranges from about 0.5 wt% to about 4 wt%, and wherein the battery has a charge final voltage that is about 4.0 V or less.

Claim 13 (withdrawn): The battery according to claim 12, wherein the amount of the maleic acid-denaturalized polyvinylidene fluoride ranges from about 0.1 wt% to about 0.4 wt%.

Claim 14 (withdrawn): The battery according to claim 12, wherein a part of the maleic acid-denaturalized polyvinylidene fluoride is substituted with hexafluoro propylene having a substitution ratio that is about 5 wt% or less.

Claim 15 (withdrawn): The battery according to claim 12, wherein the cathode active material includes lithium phosphorous oxide that has an olivine structure.

Claim 16 (withdrawn): The battery according to claim 12, wherein the cathode mixture layer contains a conductive agent including a carbon material, and wherein the content of the carbon material ranges from about 5 wt% to about 12 wt% with respect to the total amount of the cathode active material and the carbon material.

Claims 17-18 (canceled)